

# CEM III/ A42.5 N LH

| متطلبات المواصفة القياسية<br>ES 4756-1/2013<br>BS EN 197-1/2011 | النتائج       |               |               | البيان                                  |
|-----------------------------------------------------------------|---------------|---------------|---------------|-----------------------------------------|
|                                                                 | 50% GBFS      | 40% GBFS      |               |                                         |
| التركيب الكيميائي                                               |               |               |               |                                         |
|                                                                 | 30.27 %       | 27.19 %       | 25.59 %       | ثاني أكسيد السيليكون $SiO_2$            |
|                                                                 | 8.54 %        | 7.71 %        | 10.7 %        | أكسيد الألومنيوم $Al_2O_3$              |
|                                                                 | 2.39 %        | 2.68 %        | 2.31 %        | أكسيد الحديد $Fe_2O_3$                  |
|                                                                 | 49.71 %       | 52.75 %       | 48.38 %       | أكسيد الكالسيوم $CaO$                   |
|                                                                 | 3.85 %        | 3.15 %        | 6.27 %        | أكسيد المغنسيوم $MgO$                   |
| Max 4.0                                                         | 1.47 %        | 2.15 %        | 2.65 %        | كبريتات $SO_3$                          |
|                                                                 | 0.38 %        | 0.52 %        | 0.25 %        | أكسيد البوتاسيوم $K_2O$                 |
|                                                                 | 0.62 %        | 0.37 %        | 0.42 %        | أكسيد الصوديوم $Na_2O$                  |
| < 0.10                                                          | 0.018 %       | 0.03 %        | 0.03 %        | الكلور $CL$                             |
| < 2 ppm                                                         | 1.13 ppm      | 0.73 ppm      | 1.04 ppm      | الكروم السداسي $Cr^{+6}$                |
|                                                                 | 0.90 %        | 0.90 %        | 2.17 %        | المواد غير الذائبة Insoluble residue    |
|                                                                 | 1.11 %        | 1.16 %        | 1.23 %        | الفقد بالاحتراق Loss on ignition        |
| الخصائص الفيزيائية                                              |               |               |               |                                         |
|                                                                 | 4350 $cm^2/g$ | 4450 $cm^2/g$ | 4570 $cm^2/g$ | النعومة (Blaine) Fineness               |
| Max 10                                                          | 0.50 mm       | 0.50 mm       | 0.50 mm       | التمدد Expansion                        |
|                                                                 | 166 J/g       | 176 J/g       |               | Heat of Hydration 7 Days                |
| قوة الانضغاط                                                    |               |               |               |                                         |
| Min 10                                                          | 13.5 MPa      | 17.2 MPa      | 17.5 MPa      | عند ٢ يوم 2 Days                        |
|                                                                 | 23.5 MPa      | 28.3 MPa      | 28.5 MPa      | عند ٧ يوم 7 Days                        |
| Min 42.5<br>Max 62.5                                            | 43.50 MPa     | 46.5 MPa      | 45.7 MPa      | عند ٢٨ يوم 28 Days                      |
| Min 60                                                          | 195 Minutes   | 195 Minutes   | 195 Minutes   | زمن الشك الابتدائي Initial Setting Time |
|                                                                 | 255 Minutes   | 255 Minutes   | 255 Minutes   | زمن الشك النهائي Final Setting Time     |
|                                                                 | 0.62 %        | 0.60 %        | 0.34 %        | أكسيد الكالسيوم الحر Free Lime          |

## أسمنت خبث الأفران العالية سائب Blast furnace Cement



# CEM III / A 42.5 N


## أسمنت السهم

أسمنت بورتلاند خبث الأفران العالية - مقاومة إجهاد قليلة في الأيام الأولى ويتفوق على جميع أنواع الأسمنت في الأيام المتأخرة - مقاوم لأملح الكبريتات والكلوريدات - لا ينتج عن استخدامه خروج كمية حرارة عالية بعد إضافة الماء للأسمنت لذا يفضل استخدامه في الكتل الخرسانية الضخمة مثل السدود والكبارى والأنفاق

المعبأ طبقاً  
لطلب العميل



مطابق للمواصفات القياسية المصرية ١٤٧٥٦ - ٢٠١٣ /  
والمتماثلة فنياً مع المواصفات القياسية الأوروبية 1 / 2011 BS EN 197



# EC-CERTIFICATE

of Constancy of Performance  
No 0906 – CPR – 20000250012494 / 02

In compliance with Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011 (the Construction products Regulation or CPR), and also in accordance with TÜV AUSTRIA procedures, this certificate applies to the construction product:

**BLAST FURNACE CEMENT, CEM III A 42.5 N**



Placed on the market under the name  
**NATIONAL COMPANY FOR CEMENT (NCC)**

Head Office: Tower 5 Infront of Police Academy and next to the Armed Officers Club & Jewel Hotel- Zahraa Nasr City, Cairo, EGYPT

and produced in the manufacturing plant  
**NATIONAL COMPANY FOR CEMENT (NCC)**

Plant : Bayad Al Arab Industrial Zone -Beni Suef, Egypt

This certificate attests that all provisions concerning the assessment and verification of constancy of performance described in Annex ZA of the standard(s):

**EN 197-1:2011**

under system 1+ for the performance set out in this certificate are applied and that the factory production control conducted by the manufacturer is assessed to ensure the

**constancy of performance of the construction product**

This certificate was first issued on **2025-01-16** and will remain valid as long as neither the harmonised standard, the construction product, the AVCP methods nor the manufacturing conditions in the plant are modified significantly, unless suspended or withdrawn by the notified factory production control certification body or at the latest until **2028-01-15**.

Maria Agapitou  
Head of Management Systems & Products Certification Division  
Certification Body  
at TÜV AUSTRIA

Athens, **2025-05-19**

This certification was conducted in accordance with TÜV AUSTRIA auditing and certification procedures and is subject to regular surveillance audits.

TÜV AUSTRIA HELLAS  
429, Mesogeion Ave.  
GR-153 43 Athens, Greece  
[www.tuvaustriahellas.gr](http://www.tuvaustriahellas.gr)  
GEMI No.: 1650201000



CePRK525e

Headquarters in Athens bear the responsibility of the Certification decision